



**BG SYS HT Ltd.
Holubova 389
530 03 Pardubice
Czech Republic
11**

EN 1504-3

Concrete Reparatons Compound
BG QUICK[®]

Compression strength: Class R3

Chloride ions' content: $\leq 0.003\%$

Cohesiveness: ≥ 1.5 MPa

Modulus of elasticity: 28.6 GPa

Thermal compatibility - Part 1: ≥ 1.5 MPa

Antiskid properties: Class I, III

Dangerous compounds' releasing: Meets 5.4.

Fire response: Class A1

EN 13529

Chemical resistance: All salts, petroleum
products, weak acids and
alkalis, vivers (bier, wine, milk)

Imperviousness: Impervious for water
and petroleum products